

PERFORMANCE DATA							
Product Type	HEAT Reduced By	GLARE Reduced By	UV Protection	Reflectivity	Heat Absorption	Shading	Uvalue
<b>1. Reflective High Performance Window Films</b>							
Silver 15% Reflective	79%	85%	99%	High	35%	.24	.94
Silver 15% Low E Reflective	80%	83%	99%	High	37%	.24	.79
Silver 35% Reflective	65%	68%	99%	Medium	33%	.36	.99
Silver 50% Reflective	50%	58%	99%	Low	54%	.53	.97
Bronze 15% Reflective	76%	92%	99%	High	55%	.28	.94
Grey 15% Reflective	74%	93%	99%	High	58%	.29	.94
Blue 15% Reflective	72%	88%	99%	High	52%	.29	.94
Gold 15% Reflective	78%	86%	99%	High	39%	.24	.94
Green 15% Reflective	73%	86%	99%	High	48%	.31	.100
<b>2. Non-Reflective Window Firms (Dyed Films)</b>							
Grey 5% Non-Reflective	55%	95%	99%	Medium	48%	.31	1.00
Grey 20% Non-Reflective	40%	80%	99%	Low	47%	.66	1.02
Grey 35% Non-Reflective	38%	65%	99%	Low	37%	.76	1.03
Grey 50% Non-Reflective	31%	50%	99%	Low	31%	.81	1.09
Bronze 20% Non-Reflective	45%	77%	99%	Medium	39%	.74	1.14
Bronze 40% Non-Reflective	38%	60%	99%	Low	31%	.80	1.15
<b>3. Sputter High Performance Premium Window Films</b>							
Neutral 20%	67%	80%	99%	Medium	51%	.43	1.03
Neutral 35%	60%	65%	99%	Low	43%	.43	1.4
Neutral 40%	53%	60%	99%	Low	40%	.65	1.5
Neutral 50%	47%	50%	99%	Low	38%	.46	1.6
Neutral 65%	41%	40%	99%	Very Low	39%	.46	1.6
Sputter Bronze 20%	77%	75%	99%	Medium	50%	.42	1.03
Sputter Bronze 35%	66%	60%	99%	Low	40%	.43	1.4
<b>4. Ceramic High Performance Window Films</b>							
Ceramic 5%	56%	88%	99%	Medium	48%	.29	1.03
Ceramic 20%	54%	75%	99%	Medium	40%	.42	1.40
Ceramic 35%	51%	60%	99%	Low	39%	.41	1.50
Ceramic 50%	45%	45%	99%	Very Low	37%	.43	1.60
<b>Other Film</b>							
Clear Film	16%	10%	99%	NIL	7%	.99	.99
White Treatment	78%	90%	99%	Low	41%	.25	1,09
Blackout	72%	100%	100%	Medium	89%	.32	1,09